




# CLARION® Green Bio

## OVERVIEW




- Readily biodegradable anti-wear hydraulic fluids formulated with premium high oleic natural esters derived from renewable resources.
- Formulated with zinc-free, ashless additives. Zinc compounds are regulated as priority pollutants under provisions of the Clean Water Act and SARA Title 313.
- Provide protection for demanding hydraulic systems, especially those operating in environmentally sensitive areas.

## FEATURES & BENEFITS



- Meet EPA Vessel General Permit (December 2013) requirements for Environmentally Acceptable Lubricants (EAL).
- Readily biodegradable.
- Zinc-free, ashless formulation with outstanding rust and corrosion protection.
- Contain inhibitors to minimize foaming and air entrainment.
- Premium anti-wear protection for vane, piston, and gear pumps, motors and other hydraulic components.
- Safer chemical ingredients list
- All components on US EPA SCIL and/or European Ecolabel LuSC


## APPLICATIONS



- Recommended for hydraulic system applications operating in environmentally sensitive areas where the use of a zinc-free, ashless, low aquatic toxicity, readily biodegradable fluid is desired.
- Marine — marine vessels, offshore and inshore rigs, tugs, dredges, dock equipment, cranes, pile-drivers, marine construction equipment.
- Forestry — scalpers, excavators, wheel loaders.
- Construction & Mining — bulldozers, graders, backhoes, conveyors, crawlers, hole drillers.
- Oil & Gas Exploration – oil and gas drilling rigs.
- Fluid monitoring through Lubealert CPM Oil Analysis is recommended to maximize service life. Moisture content should be maintained at less than 500 ppm.

**• ZINC-FREE**  
**• READILY BIODEGRADABLE**   
**• MEETS 2013 EPA VGP REQUIREMENTS**

**PROPERTIES****Typical Properties for CLARION Green Bio:**

ISO Grade	32	46	68
Material Code	633580009	633581009	633582009
Gravity, °API ASTM D4052	27.17	28	21.52
Flash Point, (COC) °C (°F) ASTM D92	200 (392)	229 (445)	256 (492)
Viscosity ASTM D445			
cSt @ 40°C	34	47.6	69
cSt @ 100°C	8.1	10.7	13.4
Viscosity Index, ASTM D2270	223	225	200
Pour Point, °C (°F) ASTM D97	-36 (-33)	-39 (-38)	-33 (-27)
Color, ASTM D1500	L0.5	L0.5	L0.5
Copper Corrosion, ASTM D130			
3 hrs @ 100°C	1A	1A	1A
Rust Test, ASTM D665A/B	Pass	Pass	Pass
Four Ball Wear ASTM D4172			
@ 40 kg, mm		0.47	
Foam Test ASTM D892			
Seq. I, ml	0-0	10-0	0-0
Seq. II, ml	20-0	30-0	20-0
Seq. III, ml	0-0	20-0	0-0
Water Separability ASTM D1401			
@ 130°F	40/40/0/30	40/40/0/30	40/40/0/30
Dielectric Strength ASTM D877			
KV, minimum	35	35	35
Certified Biobased Content:	64%	64%	64%
 Biodegradability			
ASTM D7373, %	>60	>64	>60
Vickers V-104C Pump,			
Total Ring & Vane Loss (mg)	—	Pass	—

CLARION is a registered trademark of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners. Values shown are typical values only and do not constitute a specification. The information contained herein is subject to change without notice.

Dielectric strength is extremely sensitive to humidity and contamination. Once the containers are opened, the dielectric strength cannot be expected to remain at its original value. Containers should be kept tightly sealed and stored in a dry environment.